



| Value | Unit | Wall/m | Single | Double |
|-------------------------|-------------------|--------|--------|--------|
| Elastic Section modulus | cm ³ | 1304 | 1002 | 2005 |
| Moment of inertia | cm ⁴ | 22433 | 17270 | 34540 |
| Mass | kg/m | 99 | 76.2 | 152.4 |
| Coating Area | m ² /m | 2.55 | 1.96 | 3.92 |
| Area section | cm ² | 126.5 | 97.4 | 194.8 |

| Steel grade | S 240 GP | S 270 GP | S 320 GP | S 355 GP | S 390 GP | S 430 GP | S 460 GP |
|-------------|----------|----------|----------|----------|----------|----------|----------|
| Steel class | | | | 3 | 3 | 3 | 3 |